

| DIMENSION | | | | |
|-----------|---------------|---------------------------------------|------------|-----------------|
| dimension | thickness (d) | 8 ± 0,50 mm · dmax - dmin ≤ 0,50 mm | | |
| | length | 1288 ± 0,50 mm | | |
| | width (b) | 195 ± 0,10 mm · bmax - bmin ≤ 0,20 mm | | |
| profile | long side | twin clic+ | short side | 1clic 2go pure+ |
| groove | long side | v-groove | short side | v-groove |



Heavy domestic use



Heavy commercial use

| TOLERANCE | | |
|------------------------------------|----------|-------------------------------------|
| squareness | EN 13329 | ≤ 0,20 mm |
| straightness | EN 13329 | ≤ 0,30 mm |
| micro scratch resistance | EN 13329 | ≤ MSR-B2 |
| flatness crosswise | EN 13329 | concave: ≤ 0,15% · convex: ≤ 0,20% |
| flatness length | EN 13329 | concave: ≤ 0,50% · convex: ≤ 1,00% |
| gaps between elements | EN 13329 | average: ≤ 0,15 mm · max: ≤ 0,20 mm |
| height difference between elements | EN 13329 | average: ≤ 0,10 mm · max: ≤ 0,15 mm |
| misalignment | | ± 2 mm |

| TEST | | | |
|---|-------------|--|-----------|
| abrasion resistance | EN 13329 | AC5 (≥ 6000 rpm) | |
| impact resistance | EN 13329 | small ball ≥ 70 mm · big ball ≥ 1000 mm | |
| stain resistance | group 1 & 2 | EN 13329 | grade 5 |
| | group 3 | | ≥ grade 4 |
| castor chair test | EN 13329 | no change in appearance or damage, as defined per EN 425 | |
| effect of a furniture leg | EN 13329 | no damage shall be visible, when tested with foot type 0 | |
| static indentation | EN 13329 | ≤ 0,05 mm | |
| light fastness | EN 13329 | grey scale ≥ 4 at blue wool grade 6 | |
| dimensional variations after changes in relative humidity | EN 13329 | lengthwise ≤ 0,9 mm · crosswise ≤ 0,9 mm | |
| locking strength | EN 13329 | length ≥ 1 kN/m · width ≥ 2 kN/m | |
| surface soundness | EN 13329 | ≥ 1,25 N/mm ² | |

| ENVIRONMENT | | |
|--------------------------|----------|----------|
| emission of formaldehyde | EN 16516 | class E1 |

| PHYSICAL BEHAVIOR | | |
|----------------------|------------|----------------------------------|
| fire behavior | EN 13501-1 | Bfl s1 |
| slide resistance | EN 13893 | technical class DS |
| thermal resistance | EN 12667 | 0,073 (m ² K)/W ± 15% |
| thermal conductivity | EN 12664 | 0,110 W/(m ² K) ± 15% |
| antistatic behavior | EN 1815 | body voltage ≤ 2 kV |

*For domestic use according to the conditions of guarantee. Detailed terms of guarantee: www.krono-original.com

kronosspan

Kronoflooring GmbH
Mühlbacher Straße 1
01561 Lampertswalde/Germany
Ph. +49 3522 33 30 • Fax: +49 3522 33 399
info@kronoflooring.com

The data sheet is updated regularly to meet new technological standards.
This version replaces all previous versions as well as those which are undated.
This version takes effect upon creation. Version 12/2023